

## RICHWOOD N.C. CLEAR GLOSSY OR MATT

### ➤ **Scope**

The internationally accepted method of producing N.C. Clear lacquers is to mix nitrocellulose with non-drying short oil alkyd, a plasticizer and solvents in appropriate proportion. To reduce cost for unhealthy competition, a large number of manufacturers use less of nitrocellulose and more of an alkyd. Even solvent blend (used for making clear) must be well balanced consisting of low/medium/high boiling solvents along with latent solvents and diluents. The general practice is to use maximum quantity of cheaper solvents. Such formulations, though work, yield inferior results.

Richwood N.C. Clear is a very well balanced product.

### ➤ **Areas of Application**

All metals and also wood.

### ➤ **Surface Preparation**

See the pamphlets on surface preparation of metals and surface preparation of wood.

### ➤ **Technical Data**

- APPEARANCE : Free flowing, light pale yellow liquid.
- REDUCED VISCOSITY OF N.C. 033 THINNER (1:1) : 25 to 30 seconds
- SPRAYING VISCOSITY : 22 to 25 seconds
- THINNER TO BE USED : N.C. 033 thinner
- DUST FREE TIME : 5 to 10 minutes
- THUMB IMPRESSION FREE : 40 to 50 minutes
- HARD DRY : 24 hrs.

### ➤ **Directions for Use**

Prepare the surface as recommended above. Thin down the clear to spraying viscosity. Apply three coats, each at an interval of twenty or thirty minutes. Allow to dry when after rubbing compound be used for eliminating all blemishes. Finally polish, using wax polish but preferably silicones polish.

### ➤ **Notes**

Also available as matt lacquer. Ensure, the compressed air used is totally free from moisture.

## RICHWOOD N.C. CLEAR GLOSSY OR MATT

➤ **Disclaimer**

The information contained within this data sheet is based on information believed to be reliable at the time of its preparation. The company will not be liable for loss or damage howsoever caused including liability for negligence which may be suffered by the user of the data contained herein. It is the users' responsibility to conduct all necessary tests to confirm the suitability of any product or system for their intended use. No guarantee of results is implied since conditions of use are beyond our control.